

Special Notes----->	VOA			SYS Flush*
Mileage between changes	0	22,798	8,972	0
Mileage of fluid change	0	22,798	31,770	31,770
Aluminum	0	10	15	3
Chromium	0	0	0	0
Iron	0	53	66	15
Copper	0	70	106	22
Lead	0	16	30	7
Tin	0	6	5	3
Molybdenum	0	0	0	0
Nickel	0	0	0	0
Manganese	0	15	14	3
silver	0	0	0	0
Titanium	0	0	0	0
Potassium	0	2	3	0
Boron	119	114	88	184
Silicon	1	13	15	6
Sodium	0	9	13	7
Calcium	29	687	525	263
Magnesium	0	3	2	1
Phosphorus	264	717	650	572
Zinc	1	12	11	4
Barium	0	1	1	0

SUS Viscosity @ 210F	50	45.9	46.1	47.8
cST Viscosity @ 100C	7.26	6	6.08	6.61
Flashpoint F	430	385	400	415
water	0	0	0	0
Insolubles	0	0	0	0

PPM/1k	PPM/1k	PPM/1k
22,798	8,972	0
22,798	31,770	31,770
0.439	0.658	0.334
0.000	0.000	0.000
2.325	2.895	1.672
3.070	4.650	2.452
0.702	1.316	0.780
0.263	0.219	0.334
0.000	0.000	0.000
0.000	0.000	0.000
0.658	0.614	0.334
0.000	0.000	0.000
0.000	0.000	0.000

* Sys Flush was with Mobil 1 Synthetic ATF MB approved Sheet 236.1, 236.2, 236.5, 236.6, 236.7, 236.9